



HAND-TUFTED SPECIFICATIONS

100% NEW ZEALAND WOOL

DENSITY: 4.5 LB.

| | | | | |
|---------------------------|----------------------------|-------------------|--------------------|--------|
| Construction | Hand-Tufted | | | |
| Yarn Content | 100% New Zealand Wool | | | |
| Yarn Count | 380/1 tex | 1/80 Dewsbury | | |
| Yarn Twist | /m | 130 "Z" Direction | | |
| Ply Twist | /m | 114 "S" Direction | | |
| Dye Method | Skein | | | |
| Pile Weight | g/m ² | 2443 | oz/yd ² | 72 |
| Total Weight | g/m ² | 3750 | oz/yd ² | 110.6 |
| Pile Height | mm | 10 | in | 0.394" |
| Number of Rows | /10cm | 20 | | |
| Number of Stitches | /10cm | 26 | | |
| Number of Ends/Insertions | 4 | | | |
| Primary Backing | 67% Polyester / 33% Cotton | | | |
| Secondary Backing | Cotton Mesh | | | |
| Latexing | Natural Latex Compound | | | |

| | | | |
|-----------------------|-----------------------|----------------------------------|--|
| Fire Classification | Cfl-s1 | | |
| Flame Spread Rating | EFL | Fs ≤ 150mm within 20 seconds | |
| Optical Smoke Density | ASTM E662 / NFPA 258 | 450 or less | |
| Critical Radiant Flux | NFPA Classification 1 | 0.45 W/cm ² or higher | |

