



HAND-TUFTED SPECIFICATIONS

100% NEW ZEALAND WOOL

DENSITY: 6.5 LB.

Construction	Hand-Tufted			
Yarn Content	100% New Zealand Wool			
Yarn Count	380/1 tex	1/80 Dewsbury		
Yarn Twist	/m	130 "Z" Direction		
Ply Twist	/m	114 "S" Direction		
Dye Method	Skein			
Pile Weight	g/m ²	3529	oz/yd ²	104
Total Weight	g/m ²	4830	oz/yd ²	142.5
Pile Height	mm	13	in	0.512"
Number of Rows	/10cm	19		
Number of Stitches	/10cm	26		
Number of Ends/Insertions	5			
Primary Backing	67% Polyester / 33% Cotton			
Secondary Backing	Cotton Mesh			
Latexing	Natural Latex Compound			

Fire Classification	Cfl-s1		
Flame Spread Rating	EFL	Fs ≤ 150mm within 20 seconds	
Optical Smoke Density	ASTM E662 / NFPA 258	450 or less	
Critical Radiant Flux	NFPA Classification 1	0.45 W/cm ² or higher	

